



# SC-687

## RUST BLOCK



\*\*\*\*\*

### DESCRIPTION:

SC-687 IS A TEMPORARY CHEMICAL COATING TO CONTROL FLASH RUST ON FERROUS METALS DURING WET SAND BLASTING. SIMPLY RUN AT THE RATE OF 1 PART **SC-687** TO 50 PARTS WATER DURING WET SAND BLASTING. AS WATER SHEETS OFF METAL, NO FLASH RUSTING OCCURS. SC-687 WILL ENSURE A UNIFORM COATING ON MILD STEEL, CARBON STEEL, ALUMINUM AND ZINC COATED STEEL. SC-687 RETARDS RUSTING OF PAINTED SURFACES WHEN SCRATCHED. AN EASY-TO-CONTROL LIQUID, SC-687 REDUCES EQUIPMENT REQUIREMENTS. INJECT OR METER SC-687 INTO WATER SERVICING THE WET SAND BLASTING EQUIPMENT STRAIGHT FROM DRUM. SC-687 PERFORMS READILY IN HARD OR SOFT WATER AND NO SCALING OF TANKS OR HEATING COILS.

### TYPICAL PROPERTIES:

PHYSICAL APPEARANCE..... CLEAR, SLIGHT RED LIQUID  
ODOR..... NONE  
SPECIFIC GRAVITY... 1.06 @ 20 DEGREES C (68 DEGREES F)  
ph..... 8.5 @ 20 DEGREES C (68 DEGREES F)  
VISCOSITY..... 1.6 cps @ 20 DEGREES C (68 DEGREES F)  
FREEZE POINT..... -5 DEGREES C (23 DEGREES F)  
PHOSPHOROUS AS % P..... NONE  
FLASH POINT..... NONE

### DIRECTIONS:

SC-687 MAY BE APPLIED WITH HIGH PRESSURE WASHERS, STEAM CLEANERS OR SAND BLASTING. MIX 1 PART OF SC-687 TO 50 PARTS OF WATER THAT SERVICES THE WET SAND BLASTERS.

CONTAINS INORGANIC BUILDERS AND BIODEGRADABLE DETERGENTS. AVOID CONTINUED INHALATION OF MISTS IN SPRAYING OR OTHER APPLICATIONS. WEAR GOGGLES AND RUBBER GLOVES WHEN USING.

FIRST AID: IF EYE OR SKIN CONTACT OCCURS, FLUSH WITH LARGE AMOUNTS WATER FOR 15 MIN. FOR SKIN, FLUSH WITH WATER. IF INGESTED, GIVE WATER OR MILK. GIVE MILK OF MAGNESIA. DO NOT INDUCE VOMITING. GET MEDICAL ATTENTION IMMEDIATELY.

## ETOWAH CHEMICAL SALES & SERVICE

PO BOX 4416 \*\*\* Gadsden, Alabama 35904

1-800-848-8541